









| Product properties | | | |
|--|---------|---|---|
| Format | | 2200 x 185 x 11.5 mm | 2380 x 233 x 11.5 mm |
| Top layer | | ≥ 2.5 mm | |
| Packaging | Pack: | 10 Elements 4.07 m ² / 29.30 kg | 7 Elements 3.882 m ² / 24.000 kg |
| | Pallet: | 32 Packs 130.24 m ² / 937.60 kg | 36 Packs 139.752 m ² / 860.000 kg |
| Guarantee (according to Parador guarantee conditions) | | | 15 years (domestic area) |
| Notes | | | - cleaning and maintenance see instructions - technical changes reserved |






Product labelling

| | | | | |
|--|--|--|--|---|
|  EN 14342:2013 |  |  |  www.blauer-engel.de/uz176 |  |
|  Qualität Fertigung überwacht Funktionalität www.tuv.com ID: 0006057515 |  PEFC® PEFC04-31-0507 |  THIRD-PARTY VERIFIED ISO 14025 and EN 15804 Institut Basen und Umwelt e.V. |  | |




Tolerances (EN 13489)

| | |
|---|-----------|
| Admissible difference in length (± 0.1 %) | ± 0.05 % |
| Admissible difference in width (± 0.2 mm) | ± 0.1 mm |
| Squareness of the elements (≤ 0.2 %) | ≤ 0.05 % |
| Longitudinal curvature along the element (≤ 0.1 %) | ≤ 0.05 % |
| Transverse curvature across the width (≤ 0.2 %) | ≤ 0.08 % |
| Height differences of elements (≤ 0.2 mm) | ≤ 0.18 mm |
| Moisture content at the time of first delivery (5-9%) | 6 – 8 % |

Classification general product features

| | Test method | Rating |
|---|-------------|---|
|  Resistance to roller castor chairs | EN 425 | We recommend the use of a conventional chairmat |
|  Moving a furniture leg | EN 424 | No visible changes |
|  Thermal resistance Suitable for installation over underfloor heating when using an appropriate underlay and moisture barrier. | EN 12664 | 0.077 m ² *K/W |
|  Formaldehyde (E1 = 0.1 ppm) | EN 717-1 | ≤ 0.05 ppm |
|  Acoustical - Impact noise reduction | ISO 717-2 | 14 dB (with Akustik-Protect 100) |
| Disposal | | EAK-Code-number 20 01 38 |

Classification surface characteristics

| | Test method | Rating | |
|--|--------------|--------------------|-------------------|
| | | Lacquer | Natural oiled |
|  Slip resistance | EN 13893 | μ ≥ 0.47 | μ ≥ 0.47 |
| | CEN/TS 15676 | 29 SRT (SRV wet) | 46 SRT (SRV wet) |
| | | 51 SRT (SRV dry) | 103 SRT (SRV dry) |
|  Reaction to fire, click-installation as a floating floor | EN 13501-1 | D _{fl} s1 | |
| | EN 13501-1 | D _{fl} s1 | |
|  Chemical resistance | EN 13442 | Category 5 | Category 4 |
| Bond strength / Cross cutting test | ISO 2409 | 0 | n.n. |
| Slip resistance, inclined plane | DIN 51130 | R 9 | R 10 |

| | | | |
|--|------------|-------------------|--|
| Changed: | QMB | File name: | PA_TDS_Parkett_Basic_EN_20210201 |
| Date: | 01.08.2013 | Latest update at: | www.parador.eu/service/catalogues-downloads/technical-data-sheets |
| Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from: | | | 01.02.2021 |

| Free sorting according to EN 13489 | | | | | | | | | |
|--|--|---------------------------------------|---|------------------------|---|---------------------------------------|------------------------|------------------------|--|
| Assortment: | Block | | | | | | | | |
| Characteristics according to EN 1310: | Upper side of the lamella | | | | | | | | |
| Type of wood: | Canadian maple | European maple | Beech | | Oak | | | European cherry | American walnut |
| Botanical designation / Code (EN 13556): | Acer saccharum Marsh. / ACSC | Acer pseudoplatanus L. / APCS | Fagus sylvatica L. / FASY | | Quercus petraea Liebl., Quercus robur L. / QCXE | | | Prunus avium L. / PRAV | Juglans nigra L. / JNGG |
| Shortcut / grade / date (internal): | ER-L-AHC | ER-L-BAH | ER-L-BU | | ER-L-EI | | | ES-L-KIR | ER-L-SWN |
| | Version 6 2012 | Version 6 2012 | Version 7 2014 | | Version 25 2020 | | | Version 4 2012 | Version 7 2012 |
| | A2 | A4 | A2 | A4 | A2 | A4 | N4 | A4 | A4 |
| Grade: | Nature | Rustique | Nature | Rustique | Nature | Rustique | Living | Rustique | Rustique |
| Sound sapwood | - | - | - | - | not permitted | permitted | permitted | permitted | Permitted |
| Knot (intergrown) | permitted: up to 15 mm | permitted: up to 30 mm | permitted: up to 15 mm | permitted: up to 20 mm | permitted: up to 15 mm | permitted: up to 20 mm | permitted: up to 30 mm | permitted: up to 30 mm | permitted: up to 30 mm |
| Falling out knot | not permitted | not permitted | not permitted | | permitted: up to 10 mm | permitted: up to 20 mm | permitted: up to 20 mm | not permitted | not permitted |
| Pinkknots | permitted | permitted | permitted | | permitted | | | permitted | Permitted |
| Filling | permitted | permitted | permitted | | permitted | | | permitted | permitted |
| Slight cracks / hairline cracks | not permitted | not permitted | not permitted | | not permitted | | | not permitted | Permitted |
| Sugar inclusions, mineral inclusions | permitted | - | - | | - | | | - | - |
| Bark pocket | not permitted | not permitted | not permitted | | not permitted | | | not permitted | not permitted |
| Lightning cracks | not permitted | permitted | permitted | | not permitted | permitted | | - | permitted |
| Slope of grain | no criterion | no criterion | no criterion | | no criterion | | | no criterion | no criterion |
| Healthy heart | permitted | permitted | permitted | | - | | | - | - |
| Medullary ray | permitted | permitted | permitted | | permitted | | | permitted | - |
| Discoloration, colour variation | permitted: all colours, slight discoloration | permitted: all colours, green stripes | permitted: all colours, slight blue stain | | permitted: all colours, slight discoloration | permitted: all colours, discoloration | | permitted: all colours | permitted: all colours, slight discoloration |
| White streaks | - | - | - | | not permitted | permitted | | - | - |
| Pilling sticks marking | not permitted | not permitted | not permitted | | not permitted | | | not permitted | not permitted |
| Biodeterioration (EN 1311) | not permitted | not permitted | not permitted | | not permitted | | | not permitted | not permitted |
| Non-visible parts | | | | | | | | | |
| All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor. | | | | | | | | | |
| Comment | | | | | | | | | |
| Maximum 3% of lamellas are allowed in the next lower grading. Wood is a natural product and therefore different in colour and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master. | | | | | | | | | |

| | | | |
|--|------------|-------------------|--|
| Changed: | QMB | File name: | PA_TDS_Parkett_Basic_Anhang_EN_20210201 |
| Date: | 01.08.2013 | Latest update at: | www.parador.eu/service/catalogues-downloads/technical-data-sheets |
| Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from: | | | 01.01.2021 |
| | | | Page 1 of 3 |

| Free sorting according to EN 13489 | | |
|--|---|---------------------------|
| Assortment: | Wide plank | |
| Characteristics according to EN 1310: | Upper side of the floor board | |
| Type of wood: | Oak | |
| Botanical designation / Code (EN 13556): | Quercus petraea Liebl., Quercus robur L. / QCXE | |
| Shortcut / grade / date (internal): | ER-LH-EI | |
| | Version 3 2019 | Version 10 2019 |
| | N3 | N7 |
| Grade: | Classic | Rustique |
| Sound sapwood | not permitted | permitted |
| Knot (intergrown) | permitted: up to 30 mm | permitted: up to 80 mm |
| Falling out knot | permitted: up to 25 mm | permitted: up to 60 mm |
| Pinkknots | permitted: cluster of knots | |
| Filling | permitted | |
| Slight cracks / hairline cracks | permitted | |
| Sugar inclusions, mineral inclusions | - | |
| Bark pocket | not permitted | permitted |
| Lightning cracks | permitted | |
| Slope of grain | no criterion | |
| Healthy heart | permitted | |
| Medullary ray | permitted | |
| Discoloration, colour variation | permitted: slight colour variations | permitted: all colours |
| White streaks | permitted | |
| Pilling sticks marking | not permitted | |
| Biodeterioration (EN 1311) | not permitted | |
| Non-visible parts | | |
| All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor. | | |
| Comment | | |
| Maximum 3% of lamellas are allowed in the next lower grading. Wood is a natural product and therefore different in colour and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master. | | |

| | | | |
|--|------------|-------------------|--|
| Changed: | QMB | File name: | PA_TDS_Parkett_Basic_Anhang_EN_20210201 |
| Date: | 01.08.2013 | Latest update at: | www.parador.eu/service/catalogues-downloads/technical-data-sheets |
| Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from: | | 01.01.2021 | Page 2 of 3 |

| Free sorting according to EN 13489 | | |
|--|---|---------------------------|
| Assortment: | Extra-sized wideplank | |
| Characteristics according to EN 1310: | Upper side of the floor board | |
| Type of wood: | Oak | |
| Botanical designation / Code (EN 13556): | Quercus petraea Liebl., Quercus robur L. / QCXE | |
| Shortcut / grade / date (internal): | ER-LH-EI-N3 | ER-LH-EI-N6-N7 |
| | Version 3 2019 | Version 10 2019 |
| | N3 | N7 |
| Grade: | Classic | Rustique |
| Sound sapwood | not permitted | permitted |
| Knot (intergrown) | permitted: up to 30 mm | permitted: up to 80 mm |
| Falling out knot | permitted: up to 25 mm | permitted: up to 60 mm |
| Pinkknots | permitted: cluster of knots | |
| Filling | permitted | |
| Slight cracks / hairline cracks | permitted | |
| Sugar inclusions, mineral inclusions | - | |
| Bark pocket | not permitted | permitted |
| Lightning cracks | permitted | |
| Slope of grain | no criterion | |
| Healthy heart | permitted | |
| Medullary ray | permitted | |
| Discoloration, colour variation | permitted: slight colour variations | permitted: all colours |
| White streaks | permitted | |
| Pilling sticks marking | not permitted | |
| Biodeterioration (EN 1311) | not permitted | |
| Non-visible parts | | |
| All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor. | | |
| Comment | | |
| Maximum 3% of lamellas are allowed in the next lower grading. Wood is a natural product and therefore different in colour and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master. | | |

| | | | |
|--|------------|-------------------|--|
| Changed: | QMB | File name: | PA_TDS_Parkett_Basic_Anhang_EN_20210201 |
| Date: | 01.08.2013 | Latest update at: | www.parador.eu/service/catalogues-downloads/technical-data-sheets |
| Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from: | | | 01.01.2021 |
| | | | Page 3 of 3 |